

Chemical Products	NR	SBR	IIR	EPDM	EPM	NBR	CR	CSM	FPM	PE-X	UPE	VMO	FMO	AU	PVDF	PTFE	PFA	MFA	Alum.	Bronze	Latón	A° carbón	A° inox AISI 316
Acetaldehyde	C	D	A	A	A	D	C	C	D	A	A	A	D	D	D	A	A	A	B	C	C	A	A
Acetamide	C	C	A	A	A	C	B	B	B	A	A	B	A	D	B	A	A	A	B	C	C	A	A
Acetic Acid 10% 65°C	B	B	A	A	A	C	B	B	C	B	A	A	B	C	A	A	A	A	C	C	C	C	A
Acetic Acid 30%	B	B	A	A	A	D	B	B	C	A	A	A	B	C	A	A	A	A	C	C	C	C	A
Acetic Acid 50%	C	C	A	A	A	D	D	C	D	A	A	A	B	D	A	A	A	A	C	C	C	C	A
Acetic Acid, Glacial	D	D	B	B	A	D	D	D	D	A	A	B	D	D	A	A	A	A	C	C	C	C	A
Acetic Anhydride	C	B	B	B	B	D	C	B	D	A	A	C	D	D	D	A	A	A	B	C	C	C	B
Acetone	B	B	A	A	A	D	C	A	D	A	A	B	D	C	C	A	A	A	A	A	A	A	A
Acetone Cyanohydrin	B	C	A	A	A	D	C	A	D	A	A	C	D	D	C	A	A	A	B	B	B	B	A
Acetonitrile	D	D	D	D	D	D	B	B	D	B	A	D	D	D	A	A	A	A	B	B	B	B	A
Acetophenone	C	D	A	A	A	D	C	B	D	A	A	D	D	D	C	A	A	A	C	C	C	C	C
Acetyl Acetone	C	D	B	B	B	D	C	C	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A
Acetyl Chloride	D	D	D	D	D	D	D	D	B	B	B	C	A	D	B	A	A	A	C	C	C	C	C
Acetylene	B	B	A	B	C	A	A	B	A	A	A	C	A	B	A	A	A	A	A	D	D	A	A
Acetylene Dichloride	D	D	D	D	D	D	D	A	A	A	A	D	D	C	B	A	A	A	C	C	C	C	C
Acetylene Tetra Chloride	D	D	D	D	D	D	D	D	A	A	A	D	D	D	B	A	A	A	C	C	C	C	C
Acrylonitrile	D	D	D	D	D	D	C	C	D	A	A	D	D	D	C	A	A	A	-	A	A	A	A
Adipic Acid	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	B	B	B	B	A
Air	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Alcohols, Aliphatic	A	B	A	A	A	A	A	A	A	A	A	A	C	B	A	A	A	A	A	A	A	A	A
Alcohols, Aromatic	C	D	B	C	B	C	D	B	A	A	A	D	B	D	A	A	A	A	A	B	B	B	A
Allyl Alcohol	B	B	A	B	A	A	B	A	B	A	A	A	C	D	B	A	A	A	B	A	A	A	A
Allyl Bromide	D	D	D	D	D	D	D	D	B	B	B	D	D	D	C	A	A	A	C	C	C	C	C
Allyl Chloride	D	D	D	D	D	D	D	D	B	B	B	D	D	D	C	A	A	A	C	C	C	C	C
Alum (Aluminum Potassium Sulfate)	A	A	A	A	A	A	A	A	A	A	A	A	D	B	A	A	A	A	A	B	B	C	A
Aluminum Acetate	A	A	A	A	A	A	A	A	A	A	A	D	D	B	A	A	A	A	C	C	C	C	A
Aluminum Chloride	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	C	C	C	C	C
Aluminum Fluoride	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	C	C	C	C	C
Aluminum Hydroxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A
Aluminum Nitrate	A	A	A	A	A	A	A	A	A	A	A	B	D	A	A	A	A	A	C	C	C	C	A
Aluminum phosphate	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A	C	C	C	C	A
Aluminum Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A
Amino Ethanol	B	B	A	B	A	B	C	B	D	A	A	B	D	B	C	B	B	B	-	-	-	B	A
Ammonia Gas (cold)	A	A	A	A	A	A	B	A	D	A	A	A	A	C	A	A	A	A	B	B	B	A	A
Ammonia Gas 65°C	B	C	B	B	A	C	C	B	D	B	A	A	B	D	C	A	A	A	B	B	B	A	A
Ammonia, in Water	D	C	A	A	A	B	B	B	C	A	A	A	B	A	A	A	A	A	B	C	C	C	A
Ammonia, Liquid	D	D	A	B	B	C	D	A	D	A	A	C	D	C	C	A	A	A	A	C	C	A	A
Ammonium Carbonate	A	A	A	A	A	B	A	A	C	A	A	D	D	A	A	A	A	A	B	C	C	A	B
Ammonium Chloride	A	A	A	A	A	A	A	A	A	A	A	D	D	B	A	A	A	A	C	C	C	C	C
Ammonium Hydroxide Sulfate	B	B	A	B	A	B	B	B	B	A	A	A	B	B	A	A	A	A	C	C	C	C	B
Ammonium Metaphosphate	A	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A	B	C	C	C	A
Ammonium Nitrate	A	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A	A	-	C	C	-	-
Ammonium Persulfate	A	A	A	A	A	A	A	A	A	A	A	D	D	B	C	A	A	A	C	C	C	C	A
Ammonium phosphate	A	A	A	A	A	A	A	A	A	A	A	A	D	B	A	A	A	A	B	C	C	-	-
Ammonium Sulfide	B	A	A	A	A	B	A	A	C	A	A	D	D	B	B	A	A	A	C	C	B	C	B
Ammonium Sulfite	B	A	A	A	A	B	A	A	A	A	A	D	D	B	B	A	A	A	C	C	B	C	B
Ammonium Thiocyanate	A	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	B	C	C	C	A
Ammonium Thiosulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	B
Amyl Acetate	D	D	A	B	A	D	C	C	D	A	A	D	D	C	C	A	A	A	A	B	B	B	A
Amyl Acetone	B	B	A	A	A	D	C	A	D	A	A	B	D	C	C	A	A	A	A	A	A	A	A
Amyl Alcohol	B	A	A	A	A	B	A	A	B	A	A	D	A	C	A	A	A	A	-	A	A	B	A
Amyl Borate	D	D	D	D	D	A	D	A	D	A	A	D	D	D	D	A	A	A	-	-	-	-	-
Amyl Chloride	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Amyl Chloronaphthalene	D	D	D	D	D	D	D	D	A	A	A	D	B	D	B	A	A	A	C	C	C	C	C
Amyl Oleate	D	D	B	C	C	B	D	D	A	A	A	B	B	D	A	A	A	A	A	A	A	A	A
Amyl Phenol	D	D	D	D	C	C	D	D	A	A	A	D	A	D	B	A	A	A	A	A	A	A	A
Amyl Phthalate	D	D	A	C	B	D	D	D	C	A	A	B	C	D	B	A	A	A	-	A	A	A	A
Amylamine	C	C	A	B	A	C	C	C	D	A	A	B	D	D	A	A	A	A	-	C	C	C	A
Aniline	D	D	A	A	A	D	D	B	B	A	A	D	C	C	B	A	A	A	C	C	C	C	A
Aniline Hydrochloride	B	C	A	A	A	B	B	B	A	A	A	D	B	B	B	A	A	A	-	C	C	C	C
Animals Fats	D	D	B	C	B	A	B	B	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A
Antimony Chloride	B	B	A	B	A	B	B	B	A	A	A	A	A	A	B	A	A	A	C	C	C	C	C
Antimony Pentachloride	D	D	D	D	D	D	D	D	D	B	B	A	A	A	B	A	A	A	C	C	C	C	C
Aqua regia	D	D	D	C	C	D	D	C	B	D	D	D	C	D	B	A	A	A	C	C	C	C	C
Aromatic Hydrocarbons	D	D	D	D	D	B	C	C	A	A	A	D	B	C	A	A	A	A	A	A	A	A	A
Arsenic Acid	B	B	A	A	A	B	B	A	A	A	A	A	D	A	A	A	A	A	C	C	C	C	B
Arsenic Trichloride	D	D	D	D	C	B	C	D	D	D	D	D	D	D	A	A	A	A	C	C	C	C	C
Asphalt	D	D	D	D	D	B	D	D	A	B	B	D	D	D	A	A	A	A	C	A	A	A	A
Astm 1 Oil	D	D	D	D	D	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Astm 2 Oil	D	D	D	D	D	A	C	B	A	A	A	C	A	A	A	A	A	A	A	A	A	A	A
Astm 3 Oil	D	D	D	D	D	B	D	C	A	B	A	C	A	B	A	A	A	A	A	A	A	A	A
Aviation Gasoline	D	D	D	D	D	A	C	C	A	A	A	D	A	A	A	A	A	A	A	A	A	A	A
Barium Carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	-	A	A	B	A
Barium Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	C	C	C	C	C
Barium Hydroxide	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	A	A	-	C	C	C	A
Barium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	-	B	B	A	A
Barium Sulfite	B	A	A	A	A	B	A	A	A	A	A	A	A	B	A	A	A	A	-	C	C	C	A
Beer	C	C	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A	A	A	C	A
Beet Sugar Liquors	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	-	-	-	B	A
Benzaldehyde	D	D	B	B	B	D	D	D	D	A	A	D	D	D	C	A	A	A	-	A	A	B	A
Benzene	D	D	D	D	D	D	D	D	A	A	A	D	A	D	A	A	A	A	A	A	A	A	A
Benzene Sulfonic Acid	D	D	D	D	D	D	D	D	B	B	B	D	C	D	C	B	A	A	-	B	B	C	B

Chemical Products	NR	SBR	IIR	EPDM	EPM	NBR	CR	CSM	FPM	PE-X	UPE	VMQ	FMQ	AU	PVDF	PTFE	PFA	MFA	Alum.	Bronce	Latón	A° carbon	A° inox AISI 316
Benzene Solvent (ligroma)	D	D	D	D	D	A	C	D	A	A	A	D	A	B	A	A	A	A	A	A	A	A	A
Benzoic Acid	A	A	A	A	A	B	B	A	A	B	A	B	B	D	A	A	A	A	-	C	C	-	A
Benzoic Aldehyde	D	D	B	C	B	D	C	C	D	A	A	D	D	D	B	A	A	A	-	-	-	-	A
Benzyl Acetate	D	D	A	B	A	D	B	B	D	A	A	D	D	D	C	A	A	A	-	-	-	-	-
Benzyl Alcohol	B	B	B	B	B	D	C	C	A	A	A	D	B	D	A	A	A	A	-	A	A	B	A
Bleach Liquor	D	D	A	A	A	D	D	C	A	B	A	B	A	C	A	A	A	A	C	C	C	C	A
Borax	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	A	C	A
Bordeaux Mixture	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	A	A	C	C	C	C	A
Boric Acid	A	A	A	A	A	A	A	A	A	B	A	A	A	D	A	A	A	A	B	B	B	B	A
Brandy	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	A	A	A
Brine 65°C	A	A	A	A	A	C	A	A	A	B	A	D	D	D	A	A	A	A	-	A	A	C	A
Bromine	D	D	D	D	D	D	D	D	A	D	D	D	B	D	A	A	A	A	C	C	C	C	C
Bromine Water	D	D	C	C	C	D	D	B	A	B	A	D	B	D	A	A	A	A	C	C	C	C	C
Bromo Chloro Methane	D	D	D	D	D	D	D	D	A	B	B	D	B	D	A	A	A	A	C	C	C	C	C
Bromobenzene	D	D	D	D	D	D	D	D	B	C	C	D	A	D	A	A	A	A	C	A	A	A	A
Butadiene	D	D	D	D	D	B	D	B	A	A	A	D	B	D	A	A	A	A	A	A	A	A	A
Butane	D	D	D	D	D	A	A	A	A	A	A	D	A	A	A	A	A	A	A	A	A	A	A
Butanol	A	A	A	A	A	A	A	A	A	A	A	B	A	C	A	A	A	A	-	B	B	-	A
Butter	C	C	B	B	B	A	B	A	A	A	A	B	A	D	A	A	A	A	A	A	A	A	A
Butyl Acetate	D	D	B	B	B	D	C	C	D	A	A	D	D	D	C	A	A	A	-	B	B	B	A
Butyl Acrylate	D	D	D	D	D	D	D	D	D	B	B	D	D	D	A	A	A	A	-	-	-	-	-
Butyl Aldehyde	D	C	B	C	B	D	C	C	D	A	A	D	D	D	B	A	A	A	B	C	C	A	A
Butyl Benzene	D	D	D	D	D	D	D	D	A	A	A	D	A	D	A	A	A	A	A	A	A	A	A
Butyl Benzyl Phthalate	D	D	A	B	A	D	D	D	C	A	A	D	D	D	B	A	A	A	-	A	A	A	A
Butyl Bromide	D	D	D	D	D	D	D	D	B	B	B	D	B	D	A	A	A	A	C	B	B	B	B
Butyl Butyrate	D	D	B	B	B	C	D	D	C	B	B	D	A	D	A	A	A	A	B	B	B	B	A
Butyl Carbitol	D	D	A	A	A	C	C	B	C	A	A	D	D	D	B	A	A	A	-	A	A	B	A
Butyl Chloride	D	D	C	C	C	D	D	C	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Butyl Ether	D	D	D	D	D	B	C	B	C	A	A	D	C	D	A	A	A	A	B	A	A	B	A
Butyl Ethyl Acetate	D	D	B	B	A	D	C	C	D	A	A	D	D	D	C	A	A	A	B	C	C	A	A
Butyl Ethyl Ether	D	D	D	D	D	B	C	B	C	A	A	D	C	D	A	A	A	A	B	A	A	B	A
Butyl Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	-	A	A	A	A
Butyl oleate	D	D	B	B	B	B	C	B	A	A	A	D	B	C	A	A	A	A	A	A	A	A	A
Butyl Phthalate	D	D	A	A	A	D	D	C	C	A	A	D	D	D	B	A	A	A	B	A	A	A	A
Butyl Stearate	D	D	C	B	B	B	D	D	A	A	A	D	B	C	A	A	A	A	A	A	A	A	A
Butylamine	C	C	A	B	A	D	D	C	B	A	A	C	D	D	B	A	A	A	C	C	C	C	A
Butyraldehyde	C	C	A	B	A	D	C	C	C	A	A	D	D	D	C	A	A	A	B	C	C	A	A
Butyric Acid	C	C	B	B	B	B	B	B	A	A	A	D	D	A	A	A	A	A	B	A	A	C	A
Butyric Anhydride	C	D	B	C	B	D	B	B	C	A	A	C	D	D	C	B	A	A	B	C	C	C	B
Cadmium Acetate	A	A	A	A	A	B	A	A	B	A	A	A	A	A	A	A	A	A	B	B	B	B	A
Calcium Acetate	A	A	A	A	A	B	A	A	B	A	A	A	A	A	B	A	A	A	B	B	B	B	A
Calcium Bichromate (dry)	B	A	A	A	A	B	B	A	B	A	A	A	A	B	A	A	A	A	B	B	B	B	B
Calcium Bisulfate (dry)	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	B	A
Calcium Bisulfite (dry)	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	D	C	C	C	A
Calcium Carbonate (dry)	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	B	A
Calcium Chloride (dry)	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	B	B	C	A
Calcium Hydroxide	A	B	A	B	A	A	B	A	A	A	A	A	A	C	A	A	A	A	C	C	C	C	A
Calcium Hypochlorite	D	D	A	A	A	C	D	A	A	A	A	D	A	D	A	A	A	A	C	C	C	C	B
Calcium Nitrate	A	A	A	A	A	A	A	A	A	A	A	B	A	D	A	A	A	A	C	C	B	B	A
Calcium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	B	A
Calcium Sulfide	B	B	A	A	A	B	A	A	A	A	A	B	A	B	A	A	A	A	C	C	B	C	A
Calcium Sulfite	B	B	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	C	C	B	C	A
Cane Sugar Liquors	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	-	A	A	A	A
Caprylic Acid	D	D	A	C	B	A	C	B	B	A	A	B	B	D	A	A	A	A	-	-	-	B	A
Carbitol	D	D	A	B	A	D	D	B	A	A	A	B	B	D	A	A	A	A	-	B	B	B	B
Carbitol Acetate	D	D	B	B	B	D	D	D	D	A	A	D	D	D	C	A	A	A	-	B	B	B	A
Carbolic Acid (Phenol)	D	D	B	B	A	D	D	C	A	A	A	D	A	D	A	A	A	A	-	A	A	C	A
Carbon Dioxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Carbon Disulfide	D	D	D	D	C	C	D	D	B	A	A	D	A	D	B	A	A	A	-	B	B	A	A
Carbon Tetrachloride	D	D	D	D	D	D	D	D	A	B	B	D	A	B	A	A	A	A	D	A	A	A	A
Carbon Tetrafluoride	D	D	D	D	D	D	D	D	A	A	A	D	D	D	C	A	A	A	D	A	A	A	A
Castor Oil	C	C	B	B	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Cask-Press Pressure Hydraulic ETC	A	B	A	A	A	B	A	A	C	B	A	C	C	D	A	A	A	A	C	C	C	B	A
Chloracetone	D	D	B	B	B	D	C	C	D	A	A	D	D	D	C	A	A	A	C	C	C	C	C
Chlorinated Hydrocarbons	D	D	D	D	D	D	D	D	A	A	A	D	D	D	C	A	A	A	C	C	C	C	C
Chlorine Gas Dry	D	D	D	D	D	D	D	D	A	A	A	D	A	D	A	A	A	A	C	C	C	C	C
Chlorine, Water Solns	C	C	C	C	C	C	B	C	A	A	A	C	A	C	A	A	A	A	D	C	C	C	C
Chloroacetic Acid	D	D	A	B	A	D	C	B	B	A	A	D	D	D	B	A	A	A	C	C	C	C	C
Chlorobenzene	D	D	D	D	D	D	D	D	A	B	A	D	B	D	B	A	A	A	C	C	C	C	C
Chlorobutadiene	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Chlorobutane	D	D	C	C	B	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Chloroform	D	D	D	D	D	D	D	D	A	A	A	D	B	D	B	A	A	A	C	C	C	C	C
Chloropentane	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Chlorophenol	D	D	D	D	D	D	D	D	B	A	A	D	B	D	B	A	A	A	C	C	C	C	C
Chlorosulfonic Acid	D	D	D	D	D	D	D	D	D	D	C	D	D	D	C	B	A	A	C	C	C	C	C
Chlorotoluene	D	D	D	D	D	D	D	D	A	B	A	D	B	D	C	B	B	A	C	C	C	C	C
Chrome Plating Solution	D	D	B	C	A	D	D	D	A	B	D	B	B	D	C	A	A	A	-	-	-	-	C
Chromic Acid 40°C	D	D	C	C	B	D	D	C	B	C	B	C	C	D	B	A	A	A	C	C	C	C	B
Citric Acid	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A
Coal Tar	D	D	D	D	D	A	D	B	A	D	D	D	D	D	A	A	A	A	A	A	A	A	A
Coal Tar Naphta	D	D	D	D	D	A	D	D	A	A	A	D	D	D	A	A	A	A	A	A	A	A	A
Cobalt Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	C

Chemical Products	NR	SBR	IIR	EPDM	EPM	NBR	CR	CSM	FPM	PE-X	UPE	VMQ	FMQ	AU	PVDF	PTFE	PFA	MFA	Alum.	Bronce	Latón	A° carbono	A° inox AISI 316
Coconut Oil	D	D	B	C	B	A	B	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Cod Liver Oil	D	D	A	B	B	A	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A
Coke Oven Gas	D	D	B	B	B	A	B	A	A	C	A	B	B	C	A	A	A	A	B	B	B	A	A
Copper Arsenate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A
Copper Cyanide	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A
Copper Nitrate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A
Copper Nitrite	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A
Copper Sulfide	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	C	A
Copper Carbonate	C	C	A	A	A	B	C	B	A	A	A	C	B	B	A	A	A	A	-	-	-	-	A
Copper Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	-	C
Copper Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	-	-	-	B
Corn Oil	D	D	B	B	A	A	B	B	A	A	A	A	A	A	A	A	A	A	A	B	B	B	A
Cottonseed Oil	D	D	B	C	B	A	B	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	A
Creosote	D	D	D	D	D	A	D	C	A	A	A	D	C	D	A	A	A	A	A	B	B	A	A
Cresols	D	D	D	D	D	D	D	B	A	A	A	D	B	D	A	A	A	A	A	-	-	-	B
Cresylic Acid	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	-	A	A	B	A
Crotonaldehyde	D	D	B	B	A	D	D	C	C	A	A	D	D	D	B	A	A	A	B	C	C	A	A
Cumene	D	D	D	D	D	D	D	D	A	A	A	D	B	D	B	A	A	A	-	-	-	B	B
Cyclohexane	D	D	D	D	D	A	C	C	A	A	A	D	A	B	A	A	A	A	A	A	A	A	A
Cyclohexanol	C	C	C	C	C	A	B	B	A	A	A	D	A	B	A	A	A	A	-	A	A	A	A
Cyclohexanone	D	D	A	B	A	D	D	D	B	A	A	D	D	D	B	A	A	A	-	B	B	B	A
Cyclopentane	D	D	D	D	D	A	C	C	A	A	A	D	A	B	A	A	A	A	-	A	A	A	A
Cyclopentanol	C	C	C	C	C	A	B	B	A	A	A	A	A	B	A	A	A	A	-	A	A	A	A
Cyclopentanone	D	D	B	B	B	D	D	D	D	A	A	D	D	D	B	A	A	A	-	B	B	B	A
DDT in Kerosene	D	D	D	D	D	B	D	C	A	A	A	D	B	B	A	A	A	A	C	A	A	A	A
Decaline	D	D	D	D	D	A	C	C	A	A	A	D	A	A	A	A	A	A	A	B	B	B	A
Decane	D	D	D	D	D	A	D	D	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A
Decanol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Detergent Solution	B	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	-	A	A	A	A
Diacetone Alcohol	C	C	A	A	A	D	D	A	D	A	A	D	D	D	C	A	A	A	-	A	A	A	A
Diamylamine	C	D	A	B	A	D	C	C	D	A	A	D	D	D	C	A	A	A	D	D	D	D	B
Dibromo Benzene	D	D	D	D	D	D	D	D	B	C	C	D	B	D	A	A	A	A	A	A	A	A	A
Dibutyl Sebacate	D	D	C	C	C	D	C	C	A	A	A	B	B	D	B	A	A	A	-	A	A	A	A
Dibutylamine	D	D	D	D	D	D	A	D	A	A	A	C	D	D	C	A	A	A	D	C	C	C	A
Dibutylether	D	D	D	D	D	C	D	D	C	A	A	D	C	D	B	A	A	A	C	A	-	B	A
Dibutylphthalate	D	D	B	A	A	D	D	D	C	A	A	B	C	D	B	A	A	A	-	A	A	A	A
Dichloro propane	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Dichloroacetic Acid	D	D	A	B	A	D	D	C	D	A	A	A	B	D	A	A	A	A	C	C	C	C	C
Dichlorobutane	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Dichloroethane	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Dichloroethyl Ether	D	D	D	D	D	D	D	D	B	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Dichloroethylene	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Dichlorohexane	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Dichloroisopropyl Ether	D	D	D	D	D	D	D	D	B	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Dichloromethane	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Dichloropentane	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Dicycloxylamine	D	D	D	D	D	A	D	A	B	B	D	D	D	C	A	A	A	A	D	C	C	C	A
Diesel Oil 65°C	D	D	D	D	D	A	A	C	A	B	A	D	A	A	A	A	A	A	A	A	A	A	A
Diethanolamine	B	B	A	B	A	D	C	C	D	A	A	B	D	D	C	A	A	A	D	C	C	C	A
Diethyl Benzene	D	D	D	D	D	C	D	D	A	A	A	D	C	D	A	A	A	A	A	A	A	A	A
Diethyl Oxalate	B	B	A	A	A	D	D	D	C	A	A	D	D	D	A	A	A	A	D	B	B	B	A
Diethyl Phthalate	C	C	B	A	A	D	D	D	C	A	A	B	C	D	B	A	A	A	-	A	A	A	A
Diethyl Sebacate	D	D	A	A	A	C	D	D	C	A	A	B	B	D	B	A	A	A	-	A	A	A	A
Diethyl Sulfate	D	D	B	B	B	C	D	D	A	A	A	D	D	D	A	A	A	A	D	-	-	-	A
Diethylamine	B	B	B	B	A	D	A	C	D	A	A	B	D	D	C	A	C	A	-	C	C	C	A
Diethylenetriamine	B	B	A	B	A	D	A	C	D	A	A	B	D	D	C	A	C	A	-	C	C	C	A
Dihydroxyethyl Amine	B	B	A	A	A	D	A	C	D	A	A	B	D	D	C	A	C	A	-	C	C	C	A
Dihydroxyethyl Ether	A	A	A	A	A	D	D	A	A	A	A	D	B	D	A	A	A	A	-	C	C	C	A
Diisobutyl Ketone	D	D	B	B	A	D	D	D	D	A	A	D	D	D	B	A	A	A	A	A	A	A	A
Diisobutylene	D	D	D	D	D	A	D	D	A	A	A	D	C	D	A	A	A	A	A	A	A	A	A
Diisodecyl Adipate	D	D	B	B	B	D	D	D	C	A	A	C	C	D	B	A	A	A	-	A	A	A	A
Diisodecyl Phthalate	D	D	B	B	B	D	D	D	B	A	A	D	B	D	B	A	A	A	-	A	A	A	A
Diisooctyl Adipate	D	D	B	B	B	D	D	D	C	A	A	C	C	D	B	A	A	A	-	A	A	A	A
Diisooctyl Phthalate	D	D	B	B	B	D	D	D	C	A	A	C	B	D	B	A	A	A	-	A	A	C	A
Diisopropanol Amine	B	B	A	A	A	D	A	C	D	A	A	B	D	D	C	A	C	A	B	C	C	C	A
Diisopropyl Benzene	D	D	D	D	D	C	D	D	A	A	A	D	B	D	A	A	A	A	A	A	A	A	A
Diisopropyl Ether	D	D	D	D	D	B	D	D	D	A	A	D	D	B	B	A	A	A	A	A	A	A	A
Diisopropyl Ketone	D	D	A	A	A	D	D	D	D	A	A	D	D	D	B	A	A	A	A	A	A	A	A
Dimethyl Acetamide	B	B	B	A	A	D	D	D	D	A	A	D	D	D	C	A	A	A	-	C	C	C	A
Dimethyl Benzene	D	D	D	D	D	C	D	D	A	A	A	D	B	D	A	A	A	A	A	A	A	A	A
Dimethyl Benzylamine	D	D	D	D	D	D	D	D	D	A	A	D	D	D	C	A	C	A	-	C	C	C	A
Dimethyl Phenol	D	D	D	D	D	D	D	D	D	A	A	D	C	D	C	A	A	A	A	A	A	C	A
Dimethyl Phthalate	D	D	A	A	A	D	D	D	B	A	A	D	B	D	B	A	A	A	-	A	A	A	A
Dimethyl Sulfate	D	D	B	B	B	D	D	D	A	A	A	D	D	D	A	A	A	A	D	-	-	-	A
Dimethyl Sulfide	D	D	C	B	B	D	D	D	A	B	B	D	D	D	A	A	A	A	-	-	-	-	A
Dimethylamine	B	C	A	C	C	D	A	C	A	A	A	B	D	D	C	A	C	A	B	C	C	C	A
Dimethylaniline	D	D	C	B	B	D	D	D	D	A	A	D	D	D	C	A	C	A	C	C	C	C	A
Dimethylformamide (DMF)	D	D	C	C	C	C	D	C	D	A	A	B	D	D	B	A	A	A	A	B	B	B	A
Dinitrobenzene	D	D	C	C	B	D	D	D	D	A	A	D	D	D	B	A	A	A	-	B	B	A	A
Dinitrotoluene	D	D	D	D	D	D	D	D	C	A	A	D	D	D	B	A	A	A	-	B	B	A	A
Diocetyl Adipate (DOA)	D	D	B	B	B	D	D	D	C	A	A	C	D	D	A	A	A	A	-	A	A	A	A
Diocetyl Phthalate	D	D	B	B	B	D	D	D	C	A	A	C	B	D	B	A	A	A	-	A	A	C	A

Chemical Products	NR	SBR	IIR	EPDM	EPM	NBR	CR	CSM	FPM	PE-X	UPE	VMQ	FMQ	AU	PVDF	PTFE	PFA	MFA	Alum.	Bronce	Latón	A°. carbono	A°. Inox AISI 316
Diocetyl Sebacate	D	D	B	B	B	D	D	D	B	A	A	C	C	D	B	A	A	A	-	A	A	A	A
Diocylamine	C	C	B	B	B	C	D	C	A	A	A	B	D	D	C	A	C	A	B	C	C	C	A
Dioxane	D	D	B	B	B	D	D	D	D	A	A	D	D	D	B	A	A	A	-	A	A	A	A
Dipentene (limonene)	D	D	D	D	D	D	D	D	A	A	A	A	D	D	A	A	A	A	-	-	-	-	A
Diphenyl (Biphenyl)	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	-	B	B	A	A
Diphenyl Oxide (Phenyl Ether)	D	D	D	D	D	D	D	D	A	A	A	C	B	D	A	A	A	A	-	A	A	-	A
Diphenyl Phthalate	D	D	B	B	B	D	D	D	C	A	A	C	B	D	B	A	A	A	-	A	A	C	A
Dipropyl Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	A	A
Dipropyl Ketone	D	D	A	A	A	D	D	D	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A
Dipropylamine	B	B	A	A	A	D	D	C	A	A	A	B	D	D	C	A	C	A	B	C	C	C	A
Divinyl Benzene	D	D	D	D	D	D	D	D	A	A	A	D	D	D	A	A	A	A	A	A	A	A	A
Dodecyltoluene	D	D	D	D	D	B	D	D	A	A	A	D	B	B	A	A	A	A	A	A	A	A	A
Dodecylbenzene	D	D	D	D	D	B	D	D	A	A	A	D	A	B	A	A	A	A	A	A	A	A	A
Dow-pan (perchloroethylene)	D	D	D	D	D	C	D	D	A	B	B	D	B	D	A	A	A	A	C	B	B	B	A
Epichlorohydrin	D	D	B	B	B	D	D	D	D	B	B	D	D	D	C	A	A	A	C	C	C	C	B
Ethanolamine	B	B	A	A	A	D	B	C	D	A	A	B	D	D	C	A	C	A	B	C	C	C	C
Ethers	D	D	C	D	C	D	C	C	C	A	A	D	C	D	B	A	A	A	B	A	A	B	A
Ethyl Acetate	D	D	B	B	A	D	D	D	D	A	A	B	D	D	C	A	A	A	B	A	A	A	A
Ethyl Acetoacetate	D	D	B	B	A	D	D	D	D	A	A	B	D	D	C	A	A	A	B	A	A	A	A
Ethyl Acrylate	D	D	B	B	A	D	D	D	D	A	A	B	D	D	A	A	A	B	A	A	A	A	A
Ethyl Benzene	D	D	D	D	D	D	D	D	A	A	A	D	A	D	A	A	A	A	A	B	B	B	A
Ethyl Benzoate	D	D	B	B	A	D	D	C	A	A	A	D	A	D	A	A	A	B	A	A	A	A	A
Ethyl Butyl Alcohol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethyl Butyl Amine	B	B	A	A	A	D	D	C	A	A	A	B	D	D	C	A	C	A	B	C	C	C	A
Ethyl Butyl Ketone	D	D	A	A	A	D	D	D	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A
Ethyl Chloride	D	D	C	C	B	D	D	B	A	A	A	D	A	D	A	A	A	A	C	C	C	C	C
Ethyl Dichloride	D	D	D	D	C	D	D	D	B	A	A	D	B	D	A	A	A	A	C	C	C	C	C
Ethyl Ether	D	D	D	D	C	D	D	D	D	A	A	D	C	D	B	A	A	A	B	A	A	B	A
Ethyl Formate	D	D	A	A	A	D	D	D	D	A	A	D	A	D	A	A	A	A	B	A	A	A	A
Ethyl Hexanol	D	D	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethyl Methyl Ketone	C	C	A	A	A	D	D	D	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A
Ethyl Oxalate	B	B	A	A	A	D	D	C	C	A	A	D	B	D	A	A	A	D	B	B	B	B	A
Ethyl Phthalate	D	D	A	A	A	D	D	D	C	A	A	B	D	D	B	A	A	A	-	A	A	C	A
Ethyl Propyl Ether	D	D	D	D	C	D	D	D	D	A	A	D	C	D	B	A	A	A	B	A	A	B	A
Ethyl Propyl Ketone	D	D	A	A	A	D	D	D	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A
Ethyl Silicate	B	B	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A	A	-	-	-	-	A
Ethyl Sulfate	D	D	B	B	B	D	D	D	A	A	A	D	D	D	A	A	A	A	D	-	-	-	A
Ethylene	D	D	D	D	D	A	C	C	A	A	A	D	A	A	A	A	A	A	A	A	A	A	A
Ethylene Chloride	D	D	D	D	D	D	D	D	A	A	A	D	C	D	A	A	A	A	C	C	C	C	C
Ethylene Diamine	C	C	A	A	A	B	B	B	B	A	A	A	D	B	C	A	C	A	B	C	C	C	A
Ethylene Dibromide	D	D	D	D	D	D	D	D	B	B	B	D	C	D	A	A	A	A	C	B	B	B	B
Ethylene Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethylene Glycol 65°C	A	A	A	A	A	B	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethylene Bromide	D	D	D	D	D	D	D	D	A	A	A	D	C	D	A	A	A	A	C	B	B	B	B
Fatty Acids	D	D	A	B	A	A	B	B	A	A	A	C	D	D	A	A	A	A	-	C	C	C	A
Ferric Bromide	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	D	C	C	C	B
Ferric Chloride	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	D	C	C	C	C
Ferric Nitrate	A	A	A	A	A	A	A	A	A	A	A	C	A	A	A	A	A	A	D	C	C	C	A
Ferric Sulfate	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	D	C	C	C	A
Ferrous Hydroxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	C	C	C	A
Ferrous Sulfate	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	D	C	C	C	A
Ferrous Chloride	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	D	C	C	C	C
Fish Oil	D	D	D	D	D	A	C	C	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Fluorine	D	D	D	D	D	D	D	D	D	D	D	D	D	D	D	B	B	A	A	B	B	A	A
Fluoroboric Acid 65°C	C	C	A	A	A	A	D	A	A	B	A	D	D	A	B	A	A	A	C	B	B	B	B
Fluosilicic Acid	A	A	A	A	A	D	D	A	C	A	A	D	D	A	A	A	A	A	C	B	B	C	B
Fluosilicic Acid 65°C	B	A	A	A	A	D	D	A	C	B	A	D	D	A	B	A	A	A	C	B	B	C	B
Formaldehyde	C	C	A	A	A	C	C	B	D	A	A	B	D	C	D	A	A	A	A	A	A	B	A
Formamide	A	A	A	A	A	D	C	A	C	A	A	D	D	D	C	A	C	A	A	B	B	B	A
Formic Acid	B	B	A	A	A	C	A	A	C	A	A	B	C	C	A	A	A	A	C	C	C	C	A
Freon 11 (trichlorofluoromethane)	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	A	A	B	A
Freon 112	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon 113	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	A	A	B	A
Freon 114	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	A	A	B	A
Freon 115	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon 12 (dichlorodifluoromethane)	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon 13	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon 14 (dichlorotrifluoromethane)	A	A	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon 21	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon 218	A	A	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon 22 (monochlorodifluoromethane)	C	C	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	C	A	A	B	A
Freon 31	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon 32	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon 502	A	A	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon BF	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon C316	A	A	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon C318	A	A	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Freon MF	D	D	D	D	D	D	D	D	D	C	D	D	D	D	B	A	A	A	D	D	D	D	A
Fuel Oil	D	D	D	D	A	D	D	D	A	A	A	D	A	A	A	A	A	A	A	A	A	A	A
Fumaric Acid	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	A	C	C	C	A
Furan	D	D	D	D	D	D	D	D	D	A	A	D	D	D	A	A	A	A	B	A	A	A	A
Furfural	D	D	B	B	A	D	C	C	D	A	A	D	D	D	A	A	A	A	B	A	A	A	A

Chemical Products	NR	SBR	IIR	EPDM	EPM	NBR	CR	CSM	FPM	PE-X	UPE	VMQ	FMQ	AU	PVDF	PTFE	PFA	MFA	Alum.	Bronze	Latón	A° carbon	A° inox AISI 316	
Lye (Sodium Hydroxide)	B	B	A	A	A	B	C	A	D	A	A	B	B	B	B	A	A	A	C	A	A	B	A	
Magnesium Acetate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	A
Magnesium Carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	A	
Magnesium Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	C	
Magnesium Hydroxide	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A	A	A	C	B	B	B	A	
Magnesium Nitrate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	B	A	
Magnesium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	B	A	
Maleic Acid	A	A	A	A	A	A	B	A	A	A	D	D	A	A	A	A	A	A	B	C	C	C	A	
Maleic Anhydride	A	A	A	A	A	A	C	A	A	A	D	D	A	A	A	A	A	A	B	C	C	C	A	
Malic Acid 65°C	A	B	D	D	C	A	D	B	A	B	A	B	A	A	A	A	A	A	B	C	C	C	A	
Manganese Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	-	A	A	B	A	
Manganese Sulfide	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	-	A	A	B	A	
Manganese Sulfite	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	-	A	A	B	A	
Mercuric Chloride	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A	A	A	C	C	C	C	C	
Mercury	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A	A	A	C	C	C	C	A	
Metanol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Methacrylic Acid	D	D	B	B	A	B	B	B	B	A	A	D	D	A	A	A	A	A	B	C	C	C	A	
Methane	D	D	D	D	D	A	C	C	A	A	A	D	B	A	A	A	A	A	A	A	A	A	A	
Methyl Acetate	D	D	A	A	A	D	C	C	D	A	A	D	D	A	C	A	A	A	A	A	B	B	-	
Methyl Acrylate	D	D	B	B	A	D	B	D	D	A	A	D	D	D	B	A	A	A	-	-	-	-	A	
Methyl Bromide	D	D	D	D	D	D	D	D	A	A	A	D	A	D	A	A	A	A	C	C	C	B	B	
Methyl Butyl Ketone	D	D	A	A	A	D	C	C	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A	
Methyl Chloride	D	D	D	D	D	D	D	D	B	B	A	D	B	D	A	A	A	A	C	C	C	C	C	
Methyl Cyclohexane	D	D	D	D	D	D	D	D	A	A	A	D	B	D	A	A	A	A	A	A	A	A	A	
Methyl Ethyl Ketone (MEK)	D	D	A	A	A	D	C	C	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A	
Methyl Etyl Ketone	D	D	A	A	A	D	C	C	D	A	A	B	D	D	C	A	A	A	A	A	A	A	A	
Methyl Formate	D	D	A	A	A	D	D	D	D	A	A	B	D	D	C	A	A	A	A	A	A	A	A	
Methyl Hexanol	D	D	C	C	C	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Methyl Isobutyl Ketone (IBK)	D	D	A	A	A	D	C	C	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A	
Methyl Isopropyl Ketone	D	D	A	A	A	D	C	C	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A	
Methyl Methacrylate	D	D	B	B	A	D	C	C	D	A	A	D	D	D	B	A	A	A	-	-	-	-	A	
Methyl propyl Ether	D	D	D	D	C	D	D	D	D	A	A	D	C	D	B	A	A	A	B	A	A	B	A	
Methyl Propyl Ketone	D	D	A	A	A	D	C	C	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A	
Methyl Salicylate	D	D	B	B	A	D	D	D	D	A	A	D	D	D	A	A	A	A	B	-	-	-	B	
Methylene Bromide	D	D	D	D	D	D	D	D	A	B	A	D	B	D	A	A	A	A	C	C	C	B	B	
Methylene Chloride	D	D	D	D	D	D	D	D	B	B	A	D	B	D	A	A	A	A	C	C	C	C	C	
Mineral Oil	D	D	D	D	D	A	C	B	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	
Motor Oil	D	D	D	D	D	A	D	D	A	A	A	D	A	A	A	A	A	A	A	A	A	A	A	
Naphta (Petroleum Ether)	D	D	D	D	D	A	D	A	A	A	D	B	A	A	A	A	A	A	A	A	A	A	A	
Naphtalene	D	D	D	D	D	D	D	D	A	A	A	D	A	D	A	A	A	A	A	A	A	A	A	
Natural Gas	D	D	D	D	D	A	C	C	A	A	A	A	C	A	A	A	A	A	A	A	A	A	A	
Nickel Acetate	A	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A	A	A	A	A	A	A	
Nickel Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	C	
Nickel Nitrate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Nickel Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	A	
Nitric Acid 10% 80°C	D	D	A	A	A	D	C	A	A	B	A	D	C	D	A	A	A	A	C	C	C	C	A	
Nitric Acid 20% 65°C	D	D	A	A	A	D	D	D	A	B	A	D	C	D	A	A	A	A	C	C	C	C	A	
Nitric Acid 30% 50°C	D	D	B	B	A	D	D	A	A	A	D	C	D	A	A	A	A	A	C	C	C	C	A	
Nitric Acid 30-65%	D	D	C	C	B	D	D	D	A	D	D	D	D	D	A	A	A	A	C	C	C	C	A	
Nitric Acid, Red Fuming	D	D	D	D	D	D	D	D	C	D	C	D	D	D	A	A	A	A	C	C	C	C	A	
Nitrobenzene	D	D	D	D	D	D	D	D	B	B	A	D	D	D	B	A	A	A	-	B	B	A	A	
Nitrogen Gas	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Nitrogen Tetraoxide	D	D	D	D	D	D	D	D	D	B	B	D	D	D	D	A	A	A	C	C	C	C	A	
Nitromethane	B	C	B	B	B	D	D	C	D	A	A	D	D	D	D	A	A	A	C	C	C	C	A	
Nitropropane	C	D	B	B	B	C	D	C	C	A	A	D	D	D	C	A	A	A	C	C	C	C	A	
Nitrous Oxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	B	A	
Octane	D	D	D	D	D	A	C	B	A	A	A	D	B	A	A	A	A	A	A	A	A	A	A	
Octanol	C	C	C	C	C	A	B	B	A	A	A	D	B	A	A	A	A	A	A	A	A	A	A	
Octyl Acetate	D	D	A	A	A	D	C	C	D	A	A	D	D	D	C	A	A	A	B	A	A	A	A	
Octyl Amine	D	D	B	B	B	C	D	C	D	A	A	B	D	D	C	A	C	A	B	C	C	C	A	
Octylene Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Oleic Acid	D	D	C	C	C	B	C	A	A	A	A	D	D	B	A	A	A	A	B	B	B	C	A	
Olive Oil	D	D	C	C	B	A	B	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Orthodichlorobenzene	D	D	D	D	D	D	D	D	B	B	A	D	C	D	A	A	A	A	C	B	B	B	B	
Oxalic Acid	B	B	A	A	A	B	B	B	A	A	A	B	A	B	A	A	A	A	C	C	C	C	A	
Oxigen	D	D	B	A	A	C	B	A	A	A	A	A	B	C	A	A	A	A	A	A	A	A	A	
Ozone	D	D	B	A	A	C	A	A	A	A	A	B	C	A	A	A	A	A	A	A	A	A	A	
P-Dichlorobenzene	D	D	D	D	D	D	D	D	B	B	A	D	C	D	A	A	A	A	C	C	C	C	C	
Palm Oil	D	D	B	B	A	A	D	A	A	A	A	D	A	A	A	A	A	A	-	C	C	C	A	
Palmitic Acid	D	D	C	C	C	A	C	C	A	A	A	D	A	A	A	A	A	A	B	B	A	B	A	
Paraffin 80°C	D	D	C	C	C	A	B	A	B	A	B	A	D	B	A	A	A	A	A	A	A	A	A	
Penaut Oil	D	D	B	B	B	A	B	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Pentane	D	D	D	D	D	A	C	B	A	A	A	D	B	A	A	A	A	A	A	A	A	A	A	
Peracetic Acid 40%	D	D	C	C	B	D	D	D	D	A	A	D	D	D	B	A	A	A	C	C	C	C	B	
Perchloroethylene	D	D	D	D	D	D	D	D	A	B	A	D	C	D	A	A	A	A	C	C	C	C	C	
Petroleum	D	D	D	D	D	A	C	B	A	A	A	D	A	A	A	A	A	A	A	A	A	A	A	
Phenol 50°C	D	D	B	C	B	D	C	C	A	A	A	D	B	D	A	A	A	A	-	A	A	C	A	
Phenolsulfonic Acid	D	D	B	C	B	D	D	D	A	B	A	D	D	D	A	A	A	A	C	C	C	C	B	
Phenyl Chloride	D	D	D	D	D	D	D	D	A	A	A	D	C	D	A	A	A	A	C	C	C	C	C	
Phenylhydrazine	C	C	B	B	A	D	D	D	A	A	A	D	D	D	A	A	A	A	A	A	A	A	A	
Phosphate Esters	D	D	A	A	A	D	C	C	D	A	A	D	D	D	C	A	A	A	-	C	C	C	A	
Phosphoric Acid	D	D	A	A	A	D	D	C	A	A	A	D	B	D	A	A	A	A	C	C	C	C	A	

Chemical Products	NR	SBR	IIR	EPDM	EPM	NBR	CR	CSM	FPM	PE-X	UPE	VMQ	FMQ	AU	PVDF	PTFE	PFA	MFA	Alum.	Bronco	Latón	A° carbono	A° inox AISI 316	
Pickling solution	D	D	B	B	A	D	D	C	A	A	A	D	D	D	A	A	A	A	C	C	C	C	A	
Picric Acid, Molten	D	D	B	B	A	C	B	B	A	B	A	D	B	C	A	A	A	A	-	C	B	B	-	A
Picric Acid, Water Soln.	D	D	B	A	A	C	B	B	A	A	A	D	B	C	A	A	A	A	-	B	B	-	A	
Pine Oil	D	D	D	D	D	A	C	C	A	A	A	D	A	A	A	A	A	A	A	C	C	C	B	A
Pinene	D	D	D	D	D	A	C	C	A	A	A	D	A	A	A	A	A	A	A	A	A	A	A	A
Piperidine	D	D	B	B	A	D	D	D	A	A	A	B	D	D	C	A	A	A	A	B	C	C	C	A
Polyethylene Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Potassium Acetate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Potassium Bicarbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Potassium Bisulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Potassium Bisulfite	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Potassium Carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Potassium Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	D	C	C	C	C
Potassium Chromate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	A	B	A
Potassium Cyanide	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A
Potassium Dichromate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	C	A
Potassium Hydroxide Water Solution	B	C	A	A	A	C	C	B	C	A	A	C	C	C	A	A	A	A	C	C	C	C	B	A
Potassium Nitrate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	B	B	A
Potassium Permanganate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	A	A
Potassium Silicate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Potassium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	A
Potassium Sulfide	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	B	C	C	C	A
Potassium Sulfite	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	C	A
Propane Gas	D	D	D	D	D	A	B	B	A	A	A	D	B	A	A	A	A	A	A	A	A	A	A	A
Propanediol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Propanol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Propyl Acetate	D	D	B	B	B	D	C	C	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A	A
Propyl Aldehyde	D	D	A	A	A	D	B	B	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A	A
Propyl Amine	D	D	B	B	B	D	C	C	A	A	A	D	D	D	C	A	C	A	B	C	C	C	C	A
Propyl Chloride	D	D	D	D	D	D	D	B	B	A	D	B	D	D	C	A	A	A	C	C	C	C	C	A
Propylene Diamine	D	D	B	B	B	D	B	B	D	A	A	D	D	D	C	A	C	A	B	C	C	C	C	A
Propylene Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Pyranol	D	D	D	D	D	A	C	B	A	A	A	D	B	A	A	A	A	A	A	A	A	A	A	A
Pyridine	D	D	C	C	B	D	D	D	D	A	A	D	D	D	C	A	A	A	A	B	B	B	B	B
Rhum	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Salicylic Acid	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	-	B	B	C	A	A
Salt Water (Sea Water)	A	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sewage	B	B	A	A	A	C	B	A	A	A	A	D	B	C	A	A	A	A	B	C	C	B	A	A
Silicone Oils	A	A	A	A	A	A	A	A	A	A	A	D	A	A	A	A	A	A	A	A	A	A	A	A
Silicon Greases	A	A	A	A	A	A	A	A	A	A	A	C	A	A	A	A	A	A	A	A	A	A	A	A
Silver Nitrate	A	A	A	A	A	C	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A	A
Soda Caustic 65% (Sodium Hydroxide)	C	C	A	A	A	B	A	A	A	A	A	B	B	B	A	A	A	A	C	C	C	C	B	A
Sodium Acetate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A
Sodium Aluminate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	C	C	A	A
Sodium Bicarbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	C	C	A
Sodium Bichromate	C	C	A	A	A	B	B	A	A	A	A	A	A	A	A	A	A	A	B	C	C	C	A	A
Sodium Bisulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	C	C	C	A	A
Sodium Bisulfite	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	C	A
Sodium Borate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	C	A
Sodium Chromate	C	C	A	A	A	B	B	A	A	A	A	B	A	B	A	A	A	A	B	A	B	B	C	A
Sodium Cyanide	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	-	A	C	A	A	A
Sodium Fluoride	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	-	A	A	C	A	A
Sodium Hypochlorite	D	D	B	B	B	D	C	B	A	A	A	B	B	B	A	A	A	A	C	C	C	C	C	A
Sodium Metaphosphate	A	A	A	A	A	A	A	A	A	A	A	D	A	C	B	A	A	A	C	C	C	C	C	A
Sodium Nitrate Water Solution	A	A	A	A	A	A	A	A	A	A	A	D	C	A	A	A	A	A	A	A	A	A	A	A
Sodium Nitrite Water Solution	A	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A
Sodium Peroxide Water Solution	B	B	A	A	A	B	B	B	A	A	A	B	A	B	A	A	A	A	-	C	C	B	A	A
Sodium phosphate Water Solution	A	A	A	A	A	A	A	A	A	A	A	D	B	B	A	A	A	A	B	B	B	B	A	A
Sodium Silicate	A	A	A	A	A	A	A	A	A	A	A	D	D	A	A	A	A	A	-	C	C	A	A	A
Sodium Sulfate Water Solution	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	A
Sodium Sulfide Water Solution	B	B	A	A	A	B	A	A	A	A	A	A	B	A	A	A	A	A	-	C	C	A	A	A
Sodium Sulfite Water Solution	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A
Sodium Thiosulfate Water Solution	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	C	A	A
Soybean Oil	D	D	D	D	D	A	C	C	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Stannic Chloride	A	A	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	C	C	C	C	C	A
Stannic Sulfide	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A	A
Stannous Chloride	A	A	A	A	A	A	A	A	A	A	A	B	B	A	A	A	A	A	C	C	C	C	C	A
Stannous Sulfide	B	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	A	A
Steam Over 120°C	D	D	A	A	A	B	D	D	D	D	D	D	D	D	A	A	A	A	C	C	C	C	A	A
Steam Under 120°C	D	D	A	A	A	A	D	D	D	D	D	D	D	D	A	A	A	A	A	A	A	A	A	A
Stearic Acid	C	C	B	B	A	D	B	B	A	A	A	B	D	D	A	A	A	A	B	B	B	C	A	A
Stoddards Solvent	D	D	D	D	D	A	C	C	A	A	A	D	A	A	A	A	A	A	A	A	A	A	A	A
Styrene	D	D	D	D	D	D	D	C	C	A	A	D	D	D	A	A	A	A	B	B	B	B	A	A
Sulfonic Acid	D	D	C	C	B	D	D	C	D	A	A	D	D	D	A	A	A	A	C	C	C	C	A	A
Sulfur Chloride	D	D	D	D	C	D	D	B	A	A	A	D	D	D	A	A	A	A	C	C	C	C	C	A
Sulfur Dioxide	D	D	B	C	B	D	C	A	A	A	A	D	D	D	A	A	A	A	A	A	A	A	A	A
Sulfur Trioxide	D	D	B	C	B	D	D	D	A	A	A	D	D	D	A	A	A	A	C	C	C	C	A	A
Sulfuric Acid 25%	C	D	A	A	A	D	B	A	A	A	A	D	D	D	A	A	A	A	C	C	C	C	A	A
Sulfuric Acid 25-50%	D	D	B	B	A	D	D	A	A	A	A	D	D	D	A	A	A	A	C	C	C	C	A	A
Sulfuric Acid 50-98%	D	D	D	D	C	D	D	C	A	A	A	D	D	D	A	A	A	A	C	C	C	C	C	A

Chemical Products	NR	SBR	IIR	EPDM	EPM	NBR	CR	CSM	FPM	PE-X	UPE	VMQ	FMQ	AU	PVDF	PTFE	PFA	MFA	Alum.	Bronce	Latón	A ^o . carbono	A ^o . inox AISI 316
Sulfuric Acid, Fuming	D	D	D	D	D	D	D	D	A	D	D	D	D	D	C	A	A	A	C	C	C	C	C
Sulfurous Acid 10-75%	D	D	A	A	A	D	D	A	A	A	A	D	D	D	A	A	A	A	B	C	C	C	A
Tannic Acid	B	B	A	A	A	B	B	A	A	A	A	B	D	B	A	A	A	A	C	A	A	C	A
Tartaric Acid	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	C	C	A
Terpinol	D	D	C	C	C	A	B	A	A	A	A	D	A	A	A	A	A	A	A	A	A	A	A
Tertiary Butyl Alcohol	C	C	C	C	B	A	A	A	A	A	B	B	A	A	A	A	A	A	A	A	A	A	A
Tetrachlorobenzene	D	D	D	D	D	D	D	D	B	B	A	D	C	D	A	A	A	A	C	C	C	C	C
Tetrachloroethane	D	D	D	D	D	D	D	D	B	B	A	D	C	D	A	A	A	A	C	C	C	C	C
Tetrachloroethylene	D	D	D	D	D	D	D	D	B	B	A	D	C	D	A	A	A	A	C	C	C	C	B
Tetrachlorometane	D	D	D	D	D	D	D	D	B	B	A	D	C	D	A	A	A	A	C	C	C	C	B
Tetrachloronaphthalene	D	D	D	D	D	D	D	D	B	B	A	D	D	D	A	A	A	A	C	C	C	C	C
Tetraethylene Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Tetrahydrofuran	D	D	D	D	C	D	D	D	D	A	A	D	D	D	B	A	A	A	B	A	A	B	A
Thionyl Chloride	D	D	D	D	D	D	D	D	B	D	D	D	D	D	A	A	A	A	C	C	C	C	C
Thiophene	D	D	D	D	C	D	D	D	A	A	A	D	D	D	B	A	A	A	B	A	A	B	A
Toluene	D	D	D	D	D	C	D	D	A	B	A	D	D	D	B	A	A	A	A	A	A	A	A
Transformer Oil (Petroleum Base)	D	D	D	D	D	A	C	B	A	A	A	D	D	A	A	A	A	A	A	A	A	A	A
Triacetin	C	C	A	A	A	D	C	B	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A
Tributyl Amine	D	D	A	A	A	D	D	C	C	A	A	D	D	D	C	A	C	A	B	C	C	C	A
Tributyl Phosphate	D	D	C	C	B	B	D	D	D	A	A	D	D	D	B	A	A	A	-	B	B	A	A
Trichloro Propane	D	D	D	D	D	D	D	D	B	B	A	D	D	D	A	A	A	A	C	C	C	C	C
Trichlorobenzene	D	D	D	D	D	D	D	D	B	B	A	D	D	D	A	A	A	A	C	C	C	C	C
Trichloroethane	D	D	D	D	D	D	D	D	B	B	A	D	D	D	A	A	A	A	C	C	C	C	C
Trichloroethylene	D	D	D	D	D	D	D	D	B	B	A	D	D	D	A	A	A	A	C	C	C	C	C
Tricresyl Phosphate TCP	D	D	B	B	A	D	D	D	D	A	A	D	D	D	B	A	A	A	-	B	B	A	A
Triethanolamine (TEA)	D	D	A	A	A	B	D	C	C	A	A	D	D	D	C	A	C	A	B	C	C	C	A
Triethylamine	D	D	A	A	A	D	D	C	C	A	A	D	D	D	C	A	C	A	B	C	C	C	A
Triethylene Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Trinitrotoluene (TNT)	D	D	D	D	D	D	D	D	A	D	D	D	D	D	A	A	A	A	B	B	B	B	A
Triphenyl Phosphate	D	D	B	B	B	D	D	D	D	A	A	D	D	D	B	A	A	A	-	B	B	A	A
Turbine Oil	D	D	D	D	D	A	C	C	A	A	A	D	D	A	A	A	A	A	A	A	A	A	A
Undecanol	D	D	C	D	C	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Urea	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	B	C	A
Varnish	D	D	D	D	D	A	C	C	A	A	A	D	D	A	A	A	A	A	A	A	A	C	A
Vaseline	D	D	C	C	C	A	B	B	A	A	A	D	D	A	A	A	A	A	A	A	A	A	A
Vegetable Oils	D	D	B	B	B	A	B	B	A	A	A	D	D	A	A	A	A	A	A	A	A	A	A
Vinegar	B	C	A	A	A	C	C	C	D	A	A	A	D	C	A	A	A	A	C	C	C	C	A
Vinyl Acetate	D	D	A	A	A	D	C	C	D	A	A	D	D	D	C	A	A	A	A	A	A	A	A
Vinyl Benzene	D	D	D	D	D	D	D	D	A	A	A	D	D	D	A	A	A	A	A	B	B	A	A
Vinyl Chloride (Monomer)	D	D	D	D	D	D	D	D	A	A	A	D	D	D	A	A	A	A	C	C	C	C	C
Vinyl Ether	D	D	D	D	D	D	D	D	D	A	A	D	C	D	B	A	A	A	B	A	A	A	A
Vinyl Toluene	D	D	D	D	D	D	D	D	A	A	A	D	D	D	A	A	A	A	B	B	A	A	A
Vinyl Trichloride	D	D	D	D	D	D	D	D	A	A	A	D	D	D	A	A	A	A	C	C	C	C	C
Water, Fresh 82°C	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	A	A	A	A	A	A	A	A
Water, Salt 82°C	B	A	A	A	A	C	A	A	A	B	A	A	A	A	A	A	A	A	C	B	C	C	A
Whiskey, Wines	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	A
Xylene	D	D	D	D	D	D	D	D	A	A	A	D	D	D	A	A	A	A	A	A	A	A	A
Zeolites	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Zinc Acetate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	A
Zinc Carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Zinc Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	C	C
Zinc Chromate	B	B	A	A	A	B	B	B	A	A	A	B	A	B	A	A	A	A	B	A	A	B	A
Zinc Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	C	C	C	A

RATING		LEGEND OF MATERIALS																						
A: Excellent service (continuous usage)	NR	NATURAL RUBBER							CSM	HYPALON							PVDF	polyvinylidene fluoride						
B: Good service (intermittent usage)	SBR	SBR							FPM	VITON							PTFE	tetrafluoroethylene						
C: Limited Service (depending on use conditions)	IIR	BUTYL RUBBER							PE-X	POLYETHYLENE CROSS-LINKED							FEP	Perfluorethylenepropylene						
D: Not suitable	EPDM	EPDM							UPE	ULTRAHIGH MOLECULAR WEIGHT POLYETHYLENE							PFA	Perfluoroalkoxy						
-: Not Tested	EPM	COPOLYMER							VMQ								MFA	Perfluormethylether						
	NBR	NITRILE RUBBER							FMQ	fluorosilicone														
	CR	NEOPRENE							AU	polyurethane														

Los datos indicados en la presente tabla de resistencia químicas, han de ser considerados exclusivamente como guías de carácter general. Por este motivo, antes de escoger un determinado producto para un uso específico, se recomienda consultar con nuestros técnicos.

La presente lista se basa sobre pruebas efectuadas en laboratorio sobre nuestros compuestos habituales, sobre datos procedentes de literatura técnica y sobre la experiencia, que no tienen en cuenta las condiciones específicas de cada caso.